

## Product Data Sheet

### ROTOTUF® RT439

#### Linear Rotomolding Polyethylene

**ROTOTUF® RT439** is a high performance, UV stabilized rotomolding resin specifically designed to offer higher stiffness than standard rotomolding resins while retaining impact resistance and ESCR.

This Hexene Copolymer improves overall mechanical properties and offers the molder greater value in their applications. These high-opacity formulations, with superior dispersion of the UV additives and durable pigments, offer excellent weatherability and long term stability.

This grade is ideally suited for outdoor applications that demand higher stiffness and superior esthetic appearance.

#### NOMINAL PROPERTIES

Density	0.939 g/ml	
Melt Index	4.2 g/10 min	
<i>Tensile (ASTM D-638)</i>		
Yield strength	2690 psi,	18.5 MPa
Elongation	720%	720%
Stress at break	2045 psi	14 MPa
<i>Flexural Modulus (ASTM D-792)</i>		
Young Modulus	109,000psi	751 MPa
1% secant	102,000psi	702 MPa
<i>ARM Impact at -40°C , 0.250"</i>	120 ft.-lbs	163 Joules
<i>ESCR, D1693, 10%Igepal</i>	>1000hrs	>1000hrs
<i>UV-stability</i>	Designed for UV8-UV10; Test underway	

Rev 1- Oct2013

[www.ingeniapolymers.com](http://www.ingeniapolymers.com)

Houston Brantford Calgary Toronto Mexico Europe Mumbai Al-Jubail

The data presented is based on tests that Ingenia Polymers believes to be reliable, but Ingenia Polymers makes no warranty or representation of any kind, expressed or implied, regarding the information given or the product described, including any warranty of fitness for particular purpose. Users should make their own assessment of our products under their own conditions and their own requirements. Nothing herein is to be taken as permission, inducement or recommendation to use our products so as to infringe on any patent.

## **Colors and availability**

### *Available as Pellets*

RT439W White resin

RT439BK Black resin

### *Available as 35 mesh powder*

RT439W-G White resin

RT439BK-G Black resin

Packaged in 20kg bags or 500Kg Gaylord boxes.